

UCLNP@SiO₂-CCH in water

Run	Angle	KCps.	ZAve	Poly	Fit	Time
1	90	358,9	182,6	0,185	0,000148	10:33:14
2	90	362,6	181,3	0,16	0,000334	10:34:22
3	90	363,8	181,7	0,143	0,000182	10:35:30
4	90	361	180,5	0,199	0,000219	10:36:38
5	90	366,4	178,3	0,181	0,000192	10:37:46
Average		362,5	180,9	0,174		
+/-		2,8	1,6	0,022		

