

UCLNP@SiO₂-PEG-Mal in water

Run	Angle	KCps.	ZAve	Poly	Fit	Time
1	90	407,2	185,5	0,266	0,000155	10:41:48
2	90	399,4	179,2	0,234	0,000294	10:42:56
3	90	390,7	176,4	0,304	0,000351	10:44:04
4	90	394	177,5	0,242	0,000156	10:45:12
5	90	396,1	177,8	0,219	0,000196	10:46:20
Average		397,5	179,3	0,253		
+/-		6,3	3,6	0,033		

