

**Polybead® Amino 0.10 Micron Microspheres in water after
soaking with [Ru(dpp)₃]TMS₂**

Run	Angle	KCps.	ZAve	Poly	Fit	Time
1	90	262,3	124,2	0,037	0,000182	15:02:00
2	90	266,6	124	0,016	0,000193	15:03:09
3	90	276,2	120,8	0,029	0,000224	15:04:17
4	90	281,2	120,2	0,042	0,000203	15:05:25
5	90	274,1	117,8	0,059	0,000235	15:06:33
Average		272,1	121,4	0,037		
+/-		7,6	2,7	0,016		

